

RISE TIME AND RESPONSE MEASUREMENTS ON A LiSOCl₂ CELL

[C. BASTIEN (SAFT) - E. LECOMTE (ETCA)]

ABSTRACT

Dynamic impedance tests have been performed on a 180Ah LiSOCl₂ cell in the frame of a short term work contract awarded by Aerospatiale as part of the Hermes space plane development work. These tests consisted of Rise Time and Response Measurements.

The Rise Time Test was performed to show the ability to deliver 4KW, in the nominal voltage range (75 - 115V), within less than 100 microseconds, and after a period at rest of 13 days.

The Response Measurements Test consisted of Step Response and Frequency Response tests.

The Frequency Response test allowed to determine the "small signal" impedance of the LiSOCl₂ cell. The cell impedance was measured for various frequencies, temperatures, intensities and depths of discharge.

The Step Response test was performed to characterize the response of the LiSOCl₂ cell to a positive or negative load step of 10A starting from various currents. The test was performed for various depths of discharge and various temperatures.

The test results were used to build a mathematical, electrical model of the LiSOCl₂ cell which are also presented.

Slides 5 to 17 give the test description and test results. Slides 18 to 25 give the electrical modelization description (for which additional comments are given hereafter). Slide 26 gives the conclusions of the presentation.

MATHEMATICAL MODEL OF THE LiSOCl₂ CELL (Slides 18 to 25)

Three models of increasing complexity are presented. Their validity is limited to the conditions of the tests presented :

- Frequency : 5 to 100 000Hz
- Temperature : 10 to 70°C (50 to 160°F)
- Depth of Discharge : 25 to 75%
- Bias Currents : 0 to 80A

The Frequency Response Tests directly give the impedance versus the frequency. The model is built on the basis of the Frequency Tests and validated and refined to match the measured Step Response.

The first model accounts for the Frequency Response when the temperature is greater or equal to 40°C (104°F) while the second one is a refinement valid also for low temperatures. Model 2 was validated by simulating its response to the Step Response Test and by comparing it to the experimental response. The validity proved to be good except for low DC currents.

MODEL 1 (Slides 18 to 19)

At temperatures greater than 40°C (104°F), all frequency responses are similar : a plateau at low frequencies and a resonance at 76 KHz.

The plateau is modeled by a Series Resistance (6mΩ) and the resonance by an R-L-C parallel cell.

R₂ of the R-L-C cell is given by the impedance at the resonance frequency : R₂ = 41 - 6 = 35mΩ. The resonance frequency F₀ is equal to $1/2\pi\sqrt{LC}$ and the ratio ΔF/F₀ is equal to $R\sqrt{C/L}$. This allows to determine L and C where L = 32nH and C = 137μF.

R₁ varies slightly with T° and I_{DC} = as I or T° increase, R₁ decreases.

MODEL 2 (Slides 20 to 22)

At low temperatures (10°C , 50°F), the impedance is higher for the low frequencies (below 2KHz), while the response is identical above 2KHz. This phenomenon is modeled by an RC parallel cell, added to Model 1.

R_3 is given by the value of the plateau : $R_3 = 30 - 6 = 24\text{m}\Omega$.
 C_2 is given by the value of the impedance at $F = 2\text{KHz}$.

Model 2 also applies at high temperatures, with $R_3 = 0\text{m}\Omega$ (Model 1).

Model 2 is validated by comparing the experimental results of the Step Response Test to the simulated results. Slide N° 22 shows a good matching when the initial DC current is greater or equal to 10A for positive or negative steps.

MODEL 3 (Slides 23 to 24)

Slide N° 23 shows that for a DC current smaller than 10A, positive and negative responses are not symmetrical.

Model 3 is similar to Model 2 (RC cell, series resistance and R-L-C cell) except that the resistance of the R-L-C cell is increased when the current measured before the application of the current step is smaller than 10A. The simulated Step Response is similar to the experimental Step Response, as shown in slide N° 24, which validates Model 3.

BATTERY MODEL (Slide 24)

The equivalent electrical model of 28 cells in a series is the electrical model of a cell with resistors and inductor values multiplied by 28 and capacitor values divided by 28.

An additional series resistance (R_4) and inductance (L_2) must be added in order to take into account the influence of the cabling between cells.

$$R_4 = 4.3\text{m}\Omega$$

$$L_2 = 1.2\mu\text{H}$$

As $R_4 \ll R_1$, R_4 can be neglected

 SAFT V	DIVISION SPACE ESPACE DEPARTMENT	1991 NASA BATTERY WORKSHOP	 ETCA
RISE TIME AND RESPONSE MEASUREMENTS ON A LiSOCl₂ CELL			
BY	C. BASTIEN SAFT (FRANCE)	E. LECOMTE ETCA (BELGIUM)	

SAFT 	DIVISION ESPACE DEPARTMENT	SPACE DEPARTMENT	RISE TIME AND RESPONSE MEASUREMENTS ON A LiSOCl ₂ CELL	 ETCA
INTRODUCTION				

* THE ELECTRICAL POWER GENERATION OF THE HERMES SPACE PLANE COMPRISSES :

- THE MAIN ELECTRICAL POWER GENERATION :
 - 2 FUEL CELL POWER PLANTS TO PROVIDE ELECTRICAL ENERGY FOR THE COMPLETE MISSION

- THE SECONDARY ELECTRICAL POWER GENERATION :
 - 2 LITHIUM BATTERIES TO PROVIDE ELECTRICAL ENERGY AS AUXILIARY SOURCES IN NOMINAL MODES AND BACK-UP SOURCES FOR EMERGENCY RE-ENTRY

SAFT		DIVISION SPACE DEPARTMENT	RISE TIME AND RESPONSE MEASUREMENTS ON A LiSOCL ₂ CELL	ETCA
▼		INTRODUCTION		2.

* A SHORT TERM WORK CONTRACT WAS AWARDED BY AEROSPATIALE TO SAFT TO DEMONSTRATE THE FEASIBILITY OF A LiSOCL₂ BATTERY DESIGN, AS PART OF THE HERMES SPACE PLANE PRELIMINARY DEVELOPMENT WORK.

* THE PROPOSED LiSOCL₂ BATTERY CONSISTS OF 28 CELLS OF 180 Ah CONNECTED IN SERIES

TOTAL ENERGY = 16.6 kWh

TOTAL MASS = 60 kg (132 lb)

TOTAL VOLUME : 54 L

S A F T 	DIVISION ESPACE SPACE DEPARTMENT	RISE TIME AND RESPONSE MEASUREMENTS ON A LiSOCl₂ CELL	
<p>* SUMMARY OF THE ELECTRICAL CHARACTERISTICS OF EACH BATTERY</p> <ul style="list-style-type: none"> - OUTPUT POWER : 0 TO 6 KW - OUTPUT VOLTAGE : 75 V < u < 115 V - REQUIRED ENERGY : 16 KWh - RISE TIME : EACH BATTERY SHALL BE ABLE TO START DELIVERING 4 KW WITHIN LESS THAN 100 MICROSECONDS AND WITH u IN THE SPECIFIED RANGE, AFTER A PERIOD AT REST OF 13 DAYS, AT T BETWEEN 15 AND 40°C (59 AND 104°F). 			

 SAFT	DIVISION ESPACE DEPARTMENT	RISE TIME AND RESPONSE MEASUREMENTS ON A LiSOCL ₂ CELL	 ETCA
INTRODUCTION			

* DYNAMIC IMPEDANCE TESTS HAVE BEEN PERFORMED ON A 180 AH LiSOCL₂ CELL :

- A RISE TIME TEST WAS PERFORMED TO SHOW THE ABILITY OF THE CELL TO MEET THE RISE TIME REQUIREMENT
- RESPONSE TESTS WERE PERFORMED IN ORDER TO BUILD A MATHEMATICAL ELECTRICAL MODEL OF THE LiSOCL₂ BATTERY

THE TESTS HAVE BEEN PERFORMED AT SAFT BY ETCA (BELGIUM) WHO ALSO PROPOSED THE MATHEMATICAL MODEL.

ETCA IS INVOLVED IN THE HERMES PROGRAM AS THE POWER SYSTEM CONTRACTOR.


S A F T	▼	DIVISION ESPACE	SPACE DEPARTMENT	RISE TIME AND RESPONSE MEASUREMENTS ON A LiSOCL ₂ CELL	ETCA
TEST DESCRIPTIONS					


* RISE TIME TEST :


- DISCHARGE AT 40A, VOLTAGE MEASUREMENT DURING THE FIRST 200 μs OF THE DISCHARGE.
- 13 DAYS REST PERIOD, DURING WHICH A 50mA DISCHARGE CURRENT IS IMPOSED IN ORDER TO AVOID THE PASSIVATION EFFECT.
- DISCHARGE AT 40A, VOLTAGE MEASUREMENT DURING THE FIRST 200 μs OF THE DISCHARGE.


S A F T		DIVISION ESPACE	SPACE DEPARTMENT	RISE TIME AND RESPONSE MEASUREMENTS ON A LiSOCl ₂ CELL	ETCA															
TEST DESCRIPTIONS																				
* RESPONSE TESTS																				
<p>THEY CONSISTED OF STEP RESPONSE AND FREQUENCY RESPONSE TESTS</p> <p>- STEP RESPONSE TEST : THE CELL VOLTAGE TO A NEGATIVE AND POSITIVE 10A STEP WAS MEASURED STARTING FROM VARIOUS CURRENTS, AT VARIOUS DOD's AND CELL TEMPERATURES.</p>																				
<table border="1"> <thead> <tr> <th colspan="2">25% DOD</th> <th colspan="2">75% DOD</th> </tr> </thead> <tbody> <tr> <td>T = 43°C</td> <td>T = 11°C</td> <td>T = 11°C</td> <td>T = 72°C</td> </tr> <tr> <td>I = 0, 1, 2, 5, 10, 20, 40, 70 A.</td> <td>I = 0, 10, 40, 70 A.</td> <td>I = 0, 10, 40, 70 A.</td> <td>I = 0, 10, 40, 70 A.</td> </tr> <tr> <td>40, 70 A.</td> <td></td> <td></td> <td></td> </tr> </tbody> </table>					25% DOD		75% DOD		T = 43°C	T = 11°C	T = 11°C	T = 72°C	I = 0, 1, 2, 5, 10, 20, 40, 70 A.	I = 0, 10, 40, 70 A.	I = 0, 10, 40, 70 A.	I = 0, 10, 40, 70 A.	40, 70 A.			
25% DOD		75% DOD																		
T = 43°C	T = 11°C	T = 11°C	T = 72°C																	
I = 0, 1, 2, 5, 10, 20, 40, 70 A.	I = 0, 10, 40, 70 A.	I = 0, 10, 40, 70 A.	I = 0, 10, 40, 70 A.																	
40, 70 A.																				

SAF T		DIVISION ESPACE	SPACE DEPARTMENT	RISE TIME AND RESPONSE MEASUREMENTS ON A LiSOCl ₂ CELL	ETCA											
TEST DESCRIPTIONS																
* RESPONSE TESTS																
<ul style="list-style-type: none"> - FREQUENCY RESPONSE TEST : A SMALL SINUSOIDAL CURRENT WAS SUPERIMPOSED ON A GIVEN CURRENT AND THE VOLTAGE RESPONSE WAS MEASURED FOR VARIOUS FREQUENCIES, TEMPERATURES, INITIAL CURRENTS AND DOD's. THIS TEST ALLOWED TO DETERMINE THE "SMALL SIGNAL" IMPEDANCE OF THE LiSOCl₂ CELL. 																
<table border="1"> <thead> <tr> <th colspan="2">25% DOD</th> <th colspan="2">75% DOD</th> </tr> <tr> <th>T = 43°C</th> <th>T = 11°C</th> <th>T = 11°C</th> <th>T = 72°C</th> </tr> </thead> <tbody> <tr> <td>I = 0, 1, 2, 5, 10, 20, 30, 40, 60, 78 A.</td> <td>I = 1, 2, 5, 10, 20, 40, 78 A.</td> <td>I = 1, 2, 78, 5, 40, 10, 20 A.</td> <td>I = 1, 2, 78, 5, 40, 10, 20 A.</td> </tr> </tbody> </table>					25% DOD		75% DOD		T = 43°C	T = 11°C	T = 11°C	T = 72°C	I = 0, 1, 2, 5, 10, 20, 30, 40, 60, 78 A.	I = 1, 2, 5, 10, 20, 40, 78 A.	I = 1, 2, 78, 5, 40, 10, 20 A.	I = 1, 2, 78, 5, 40, 10, 20 A.
25% DOD		75% DOD														
T = 43°C	T = 11°C	T = 11°C	T = 72°C													
I = 0, 1, 2, 5, 10, 20, 30, 40, 60, 78 A.	I = 1, 2, 5, 10, 20, 40, 78 A.	I = 1, 2, 78, 5, 40, 10, 20 A.	I = 1, 2, 78, 5, 40, 10, 20 A.													
FOR EACH CASE, THE FREQUENCY VARIED BETWEEN 5 Hz and 100 kHz																











1991 NASA Aerospace Battery Workshop

-200-

Primary Technologies Session


SAFT 	DIVISION SPACE ESPACE DEPARTMENT	RISE TIME AND RESPONSE MEASUREMENTS ON A LiSOCl₂ CELL	ETCA 
TEST RESULTS			
STEP RESPONSE TEST			
		AT T = 43°C, DOD = 25%, I = 0A	
			
			


SAFT DIVISION SPACE DEPARTMENT			RISE TIME AND RESPONSE MEASUREMENTS ON A LiSOCl ₂ CELL	TEST RESULTS
▼ S A F T	DIVISION ESPACE	SPACE DEPARTMENT	 ETCA	

STEP RESPONSE TESTS


- **DYNAMIC RESPONSE (0 TO 70 μ s) :**
- * WHEN $40 < T < 70^\circ\text{C}$, NEGATIVE STEP RESPONSE IS IDENTICAL FOR ALL CURRENT AND DOD.
- * WHEN $T < 40^\circ\text{C}$, THE VOLTAGE VARIATION DUE TO THE 10A STEP INCREASES AND VARIES WITH THE DOD.
- * THE POSITIVE STEP RESPONSE IS THE OPPOSITE OF THE NEGATIVE STEP RESPONSE FOR $I > 10$ A.
- * FOR $I \leq 10$ A, THE VOLTAGE VARIATION DUE TO THE POSITIVE 10 A LOAD STEP, IS HIGHER
- * THE VOLTAGE ALWAYS STABILIZED WITHIN 70 μ s WITH ΔV ALWAYS INFERIOR TO 0.13V.
- **STATIC RESPONSE :**
- * AFTER $T = 70\mu\text{s}$, THE VOLTAGE SLOWLY VARIES WITH TIME BEFORE REACHING ITS NOMINAL VALUE

 SAFT DIVISION ESPACE SPACE DEPARTMENT	 ETCA MEASUREMENTS ON A LiSOCl₂ CELL	TEST RESULTS
GENERAL OBSERVATIONS ON DYNAMIC RESPONSES OF LiSOCl₂ CELLS :		
<ul style="list-style-type: none"> - THE HIGHER THE STARTING CURRENT, THE LOWER THE VOLTAGE VARIATION DUE TO THE 10A STEP - THE HIGHER THE TEMPERATURE, THE LOWER THE VOLTAGE VARIATION DUE TO THE 10A STEP - THE LOWER THE DEPTH OF DISCHARGE, THE LOWER THE VOLTAGE VARIATION DUE TO THE 10A STEP 		





SAFT			▼	DIVISION ESPACE	SPACE DEPARTMENT	RISE TIME AND RESPONSE	MEASUREMENTS ON A LiSOCl ₂ CELL	ETCA
TEST RESULTS								
<p><u>CELL DISCHARGE</u></p> <p>DELIVERED ENERGY : 612.1 WH (400 WH/KG)</p> <p>DELIVERED CAPACITY : 204.8 AH</p>								




▼
S A F T


DIVISION
ESPACE DEPARTMENT

RISE TIME AND RESPONSE
MEASUREMENTS ON A LiSOCl₂ CELL


ELECTRICAL MODELIZATION



MODEL 1 : T ≥ 40°C




SIMULATION RESULT



R₁ = 6 mΩ TO 10 mΩ
(R₁ INCREASES AS T° AND/OR DC CURRENT DECREASES)

$$\begin{aligned}R_2 &= 35 \text{ m}\Omega \\L &= 32 \text{ nH} \\C &= 137 \text{ fF}\end{aligned}$$




S A F T

DIVISION
ESPACE DEPARTMENT


RISE TIME AND RESPONSE
MEASUREMENTS ON A LiSOCl₂ CELL

ELECTRICAL MODELIZATION

MODEL 2 : T < 40°C




SIMULATION RESULT



R₃ = 0 mΩ TO 24 mΩ
(R₃ INCREASES AS T° AND/OR DC CURRENT DECREASES)

C₂ = 35.4 mF



SAFT

DIVISION
ESPACE
DEPARTMENT


RISE TIME AND RESPONSE
MEASUREMENTS ON A LiSOCl₂ CELL




ELECTRICAL MODELIZATION


MODEL VALIDATION WITH STEP RESPONSE RESULTS ($I_{DC} < 10A$)


FOR $I < 10A$, THE POSITIVE AND NEGATIVE STEP RESPONSES ARE NOT SYMETRICAL. THE CELL VOLTAGE VARIATION DUE TO THE POSITIVE STEP IS HIGHER.



THE MODEL MUST INCLUDE A VARIABLE RESISTOR (R) WHICH WILL BE A FUNCTION OF THE CURRENT DELIVERED BY THE CELL.





 SAFT ▼	DIVISION ESPACE DEPARTMENT	SPACE MEASUREMENTS ON A LiSOCl₂ CELL	RISE TIME AND RESPONSE ETCA 
<p>CONCLUSION</p> <ul style="list-style-type: none"> * THE 180 AH LiSOCl₂ CELL HAS SHOWN THE ABILITY TO DELIVER 40A WITHIN LESS THAN 60 μs IN THE SPECIFIED VOLTAGE RANGE (> 3 VOLTS). * NO DELAY EFFECT WAS NOTICED AFTER 13 DAYS DURING WHICH A 50mA PERMANENT CURRENT WAS DISCHARGED. * SEVERAL ELECTRICAL MODELS HAVE BEEN PRESENTED WHICH SIMULATE THE DYNAMIC BEHAVIOUR OF THE CELL FOR DIFFERENT CONDITIONS OF TEMPERATURE, CURRENT AND DOD. * TWO MODELS OF THE 28 LiSOCl₂ CELL BATTERY ARE PROPOSED TO BE USED FOR THE MATHEMATICAL ANALYSIS OF THE HERMES POWER SYSTEM AND FOR AN ELECTRICAL SIMULATOR SPECIFICATION. 			

26.